

Approval body for construction products  
and types of construction

Bautechnisches Prüfamt

An institution established by the Federal and  
Laender Governments



## European Technical Assessment

**ETA-16/0430  
of 3 July 2023**

English translation prepared by DIBt - Original version in German language

### General Part

Technical Assessment Body issuing the  
European Technical Assessment:

Deutsches Institut für Bautechnik

Trade name of the construction product

WELDA ®

Product family  
to which the construction product belongs

Steel plate with cast-in anchors

Manufacturer

PEIKKO GROUP CORPORATION  
Voimakatu 3  
15101 Lahti  
FINNLAND

Manufacturing plant

Peikko Herstellwerke

This European Technical Assessment  
contains

14 pages including 3 annexes which form an integral part  
of this assessment

This European Technical Assessment is  
issued in accordance with Regulation (EU)  
No 305/2011, on the basis of

EAD 330084-01-0601, Edition 06/2023

This version replaces

ETA-16/0430 issued on 26 March 2018

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission in accordance with Article 25(3) of Regulation (EU) No 305/2011.

## Specific Part

### 1 Technical description of the product

The WELDA steel plate with welded on anchors consist of steel and stainless steel.

The anchors have a diameter of the shaft of 10, 12, 13, 16, 19, 20, 22 and 25 mm. The Anchors consists of steel, stainless steel or ribbed reinforcing steel. At one end an anchor head is formed by upsetting. The other end is prepared for drawn arc stud welding with ceramic ferrule or shielding gas or metal active gas (MAG) welding with different electrodes (method 783, method 135, method 136 and method 138 according to EN ISO 4063:2010).

The steel plates with welded on anchors are embedded surface-flush in the concrete.

The product description is given in Annex A.

### 2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the anchor of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

### 3 Performance of the product and references to the methods used for its assessment

#### 3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance to steel failure of anchors under tension load	$N_{Rk,s}$ see Annex C1
Characteristic resistance to pull-out failure under tension load	$N_{Rk,p}$ see Annex C1
Characteristic values for resistance to concrete cone failure under tension load	$h_{ef}, S_{cr,N}, c_{cr,N}, k_{cr,N}, k_{ucr,N}$ see Annex C1
Characteristic resistance to blow-out failure - Bearing area of anchor head	$A_h$ see Annex A2
Characteristic resistance to steel failure for anchors under shear load without lever arm	$V_{Rk,s}^0, k_7$ see Annex C2
Characteristic value for resistance to pry-out failure	$k_8$ see Annex C2
Displacements	$\delta_{N0}, \delta_{V0}, \delta_{N\infty}, \delta_{V\infty}$ see Annex C1 and C2

#### 3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Class A1

**4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base**

In accordance with EAD No. 330084-01-0601, the applicable European legal act is: [96/582/EC].

The system to be applied is: 1


**5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable EAD**

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited with Deutsches Institut für Bautechnik.

Issued in Berlin on 3 July 2023 by Deutsches Institut für Bautechnik

Dipl.-Ing. Beatrix Wittstock  
Head of Section

*beglaubigt:*  
Müller



**h** = thickness of concrete member

**WELDA®** = Steel plate with welded on anchors  
made of steel or stainless steel

**WELDA®**

Product description  
Installation condition

**Annex A1**

**Table 1: Materials, welding processes**

	Part	Designation	Type	Material	Mechanical properties
WELDA®	Plate	Steel plate	P1	Steel S235JR, S235J0 S235J2, S355JR, S355J0, S355J2, S355K2 according to EN 10025-2:2005	according to EN 10025-2:2005 $f_{uk} \leq 1000 \text{ N/mm}^2$
			P2	Stainless steel 1.4301 1.4303, 1.4306, 1.4307 according to EN 10088-1:2014	according to EN 10088-1:2014 $f_{uk} \leq 1000 \text{ N/mm}^2$
			P3	Stainless steel 1.4401, 1.4404, 1.4432, 1.4436, 1.4439, 1.4571 according to EN 10088-1:2014	according to EN 10088-1:2014 $f_{uk} \leq 1000 \text{ N/mm}^2$
	Anchor	Headed studs EN ISO 13918 Types SD1, SD3 Welding process 135, 136, 138 and 783 according to EN ISO 4063:2010	W1	SD1, Material group 1 with the limits: C $\leq 0,2 \%$ ; CEV $\leq 0,35$ ; Al $\geq 0,02 \%$ ISO/TR 15608:2013	$f_{uk} \geq 450 \text{ N/mm}^2$ $f_{uk} \leq 1000 \text{ N/mm}^2$ $f_{yk} \geq 350 \text{ N/mm}^2$
			W2	SD3, Stainless steel 1.4301, 1.4303 EN 10088-1:2014	$f_{uk} \geq 450 \text{ N/mm}^2$ $f_{uk} \leq 1000 \text{ N/mm}^2$ $f_{yk} \geq 350 \text{ N/mm}^2$
		Anchor bolts with smooth shaft provided with an anchor head Welding process 135, 136, 138 and 783 according to EN ISO 4063:2010	W3	Steel S235J2, S355J2 EN 10025:2011	$f_{uk} \geq 450 \text{ N/mm}^2$ $f_{uk} \leq 1000 \text{ N/mm}^2$ $f_{yk} \geq 350 \text{ N/mm}^2$
			W4	Stainless steel 1.4301 1.4303, 1.4306, 1.4307 EN 10088-1:2014	$f_{uk} \geq 450 \text{ N/mm}^2$ $f_{uk} \leq 1000 \text{ N/mm}^2$ $f_{yk} \geq 350 \text{ N/mm}^2$
			W5	Stainless steel 1.4401, 1.4404, 1.4432, 1.4436, 1.4439, 1.4571 EN 10088-1:2014	$f_{uk} \geq 450 \text{ N/mm}^2$ $f_{uk} \leq 1000 \text{ N/mm}^2$ $f_{yk} \geq 350 \text{ N/mm}^2$
		Anchor bolts of ribbed reinforcing steel provided with an anchor head Welding process 135 and 138 according to EN ISO 4063:2002	W6	Reinforcing steel B500B EN 1992-1-1:2004 +AC:2010, Annex C	$f_{uk} \geq 550 \text{ N/mm}^2$ $f_{yk} \geq 500 \text{ N/mm}^2$

**Table 2: Dimensions**

WELDA® Anchor Type		W1 – W5								W6		
Nominal size diameter of shafts	d [mm]	10	12	13	16	19	20	22	25	16	20	25
Minimum nominal diameter of anchor head	min d <sub>h</sub> [mm]	19	24	25	32	32	40	35	40	38	46	55
Bearing area of anchor head	A <sub>h</sub> [mm <sup>2</sup> ]	205	339	356	603	521	942	582	766	933	1348	1885
Thickness of the anchor head (Headed studs)	t <sub>h</sub> [mm]	7	8	8	8	10	10	10	12	-	-	-
Thickness of the anchor head (Anchor bolts)	t <sub>h</sub> [mm]	3	3	3	4	-	5	-	-	4	4	4
Nominal length of anchor	min h <sub>nom</sub> [mm]	50	50	50	50	75	75	75	75	50	75	75
	max h <sub>nom</sub> [mm]	200	200	400	525	525	525	525	525	800	800	1000

**WELDA®**


Product description  
Materials, welding processes, dimensions

**Annex A2**

**Table 3: Steel plate and anchor combinations**

	Product name	Plate	Anchors
1	WELDA®	P1	W1/W3
2	WELDA® R	P2	W1/W3
3	WELDA® Rr	P2	W2/W4
4	WELDA® A	P3	W1/W3
5	WELDA® Ar	P3	W2/W4
6	WELDA® Aa	P3	W5
7	WELDA® Strong	P1	W6
8	WELDA® Strong R	P2	W6
9	WELDA® Strong A	P3	W6

The anchors shall be butt-welded to the steel plate with fillet welds.  
Alternatively, the anchor can be inserted in a hole in the steel plate and welded with fillet welds.



Fill up completely with  
welding material

### Marking of product

Products are marked with identifying mark of producer with a product name and dimensions on the visible face of steel plate.

Example from marking



WELDA® 150 x 150 Aa

**WELDA®**

Product description  
Steel plate and anchor combinations, Product marking

**Annex A3**

## Specifications of intended use

### Loading of steel plate with welded on anchors subject to:

- Static and quasi-static tension and shear.

### Base materials:

- Reinforced compacted normal weight concrete according to EN206:2013+A2:2021 without fibres
- Strength classes C20/25 to C90/105 according to EN206:2013+A2:2021
- Cracked or uncracked concrete.

### Use conditions (Environmental conditions):

- Structures subject to dry internal conditions:  
=> steel plates and anchors acc. Annex A3, Table 3, Lines 1-9
- According to EN1993-1-4:2006 + A2:2015 relating to corrosion resistance class CRC III.  
=> steel plates and anchors acc. Annex A3, Table 3, Line 6

### Design:

- Steel plate with cast-in anchors are designed under the responsibility of an engineer experienced in anchorages and concrete work.
- Verifiable calculation notes and drawings are prepared taking account of the loads to be anchored. The position of the anchors are indicated on the design drawings (e.g. position of the anchor relative to the reinforcement or to supports).
- For static and quasi-static loading the steel plate with cast-in anchors are designed in accordance with EN1992-4:2018.
- It is generally assumed that the concrete is cracked and that the occurring splitting forces are resisted by the reinforcement. The required cross section of the minimum reinforcement is determined according EN1992-4:2018 section 7.2.1.7 b).

### Installation:

#### Placing steel plates into concrete

- The installation of anchors is carried out by appropriately qualified personnel under the supervision of the person responsible for the technical matters on site.
- Use of the product only as supplied by the manufacturer.
- Installation in accordance with the manufacturer's specifications given in Annexes B4 and B5.
- The anchorages are fixed on the formwork, reinforcement, or auxiliary construction such that no movement of the product will occur during the time of laying the reinforcement and of placing and compacting the concrete.
- The concrete under the head of the anchors is properly compacted.
- For large fixtures (steel plate > 400 mm x 400 mm) vent openings are provided, specified in the design drawings.

WELDA®

Intended use  
Specifications

Annex B1



**Table 4: Installation parameters**


WELDA® Anchor Type Nominal size d [mm]		W1 – W5								W6		
		10	12	13	16	19	20	22	25	16	20	25
Minimum effective embedment depth	min h <sub>ef</sub> [mm]	50	50	50	50	75	75	75	75	50	75	75
Minimum spacing	s <sub>min</sub> [mm]	50	50	50	50	70	70	70	70	50	70	70
Minimum edge distance	c <sub>min</sub> [mm]	50	50	50	50	70	70	70	70	50	70	70
Minimum thickness of concrete member	h <sub>min</sub> [mm]	h <sub>ef</sub> + t <sub>h</sub> + c <sub>nom</sub> <sup>1)</sup>										
1) c <sub>nom</sub> = required concrete cover according to national regulations												

**WELDA®**

Intended use  
Installation parameters


**Annex B2**

Fig. 1: Simple anchor




$$h_{ef} = h_{nom} - t_h + t \quad (1)$$

Fig. 2: Doubled anchor



$$h_{ef} = h_{nom1} + h_{nom2} - t_h + t \quad (2)$$


Fig. 3: Short anchor, if the theoretic concrete cone meets the steel plate at angle of  $\sim 60^\circ$  or  $t \geq 0,2h_{nom}$



$$h_{ef} = h_{nom} - t_h \quad (3)$$

- d** = diameter of shaft  
**d<sub>h</sub>** = diameter of head  
**h<sub>ef</sub>** = effective embedment depth  
**h<sub>nom</sub>** = nominal length of the anchor (after welding)  
**t<sub>h</sub>** = thickness of the head  
**t** = thickness of the steel plate

Alternative head form:




**WELDA®**

Intended use  
Effective embedment depth

**Annex B3**


Installation instruction

1a      Fixing WELDA® to reinforcement



- Fix WELDA® to reinforcement or to mounting bars by using wire bindings
- Pay attention to strong fixing to avoid moving during pouring

1b      Fixing WELDA® to formwork




- Fix WELDA® directly to formwork by nails, screws, wire or magnets
- Control close contact between plate and formwork
- Pay attention to strong fixing to avoid moving during pouring

**WELDA®**


Intended use  
Installation instruction

**Annex B4**


2 Check WELDA® after installation



Not allowed




Not allowed



Not allowed

3 Pouring, compacting and curing concrete, remove formwork



- Compact concrete properly around and under the steel plate and anchors
- Avoid contact between the steel plate with anchor and the vibrator to avoid moving of the steel plate during compacting

WELDA®

Intended use  
Installation instruction

Annex B5

**Table 5: Characteristic resistances under tension**

WELDA® Anchor Type		W1 – W5								W6		
Nominal size	d [mm]	10	12	13	16	19	20	22	25	16	20	25
Steel failure												
Characteristic resistance	N <sub>Rk,s</sub> [kN]	35	51	60	90	128	141	171	221	111	173	270
Partial factor	γ <sub>Ms</sub> <sup>1)</sup>	1,54								1,4		
Pull-out failure												
Characteristic resistance in uncracked concrete C20/25	N <sub>Rk,p</sub> [kN]	43	71	75	127	109	198	122	161	196	283	396
Characteristic resistance in cracked concrete C20/25	N <sub>Rk,p</sub> [kN]	31	51	54	90	78	141	87	115	140	202	283
Increasing factors ψ for N <sub>Rk,p</sub> = ψ · N <sub>Rk,p</sub> (C20/25)	C25/30	1,25										
	C30/37	1,50										
	C35/45	1,75										
	C40/50	2,00										
	C45/55	2,25										
	C50/60	2,50										
	C55/67	2,75										
	≥ C60/75	3,00										
Partial factor	γ <sub>Mp</sub> <sup>1)</sup>	1,5										
Concrete cone failure												
Effective embedment depth	h <sub>ef</sub> [mm]	h <sub>nom</sub> – t <sub>h</sub> + t <sup>3)</sup>										
Characteristic spacing	s <sub>cr,N</sub> [mm] <sup>2)</sup>	3 h <sub>ef</sub>										
Characteristic edge distance	c <sub>cr,N</sub> [mm] <sup>2)</sup>	1,5 h <sub>ef</sub>										
Factor for cracked concrete	k <sub>cr</sub> [-]	8,9										
Factor for uncracked concrete	k <sub>ucr</sub> [-]	12,7										
Partial factor	γ <sub>Mc</sub> <sup>1)</sup>	1,5										
Blow-out failure												
Partial factor	γ <sub>Mc</sub> <sup>1)</sup>	1,5										

1) In absence of other national regulations

2) Reinforcement resists the splitting forces and limits the crack width to  $w_k \leq 0,3$  mm

3) For simple anchors (For doubled anchors resp. short anchors see Fig. 2 resp. Fig. 3, Annex B3)

**Table 6: Displacements under tension**

WELDA® Anchor Type		W1 – W5								W6		
Nominal size	d [mm]	10	12	13	16	19	20	22	25	16	20	25
Tension load	$N$ [kN]	20	34	36	60	52	94	58	77	93	135	188
Displacements $\delta_{N0}$ for load $N$	$\delta_{N0}$ [mm]	0,7	0,8	1,0	1,3	1,0	1,4	1,0	1,0	0,7	0,8	0,9
Displacements $\delta_{N\infty}$ for load $N$	$\delta_{N\infty}$ [mm]	1,4	1,6	2,0	2,6	2,0	2,8	2,0	2,0	1,4	1,6	1,8

**WELDA®**

Performance data  
Characteristic resistances and displacements under tension load

**Annex C1**

**Table 7 Characteristic resistances under shear load**

WELDA® Anchor Type		W1 – W5								W6		
Nominal size	d [mm]	10	12	13	16	19	20	22	25	16	20	25
<b>Steel failure</b>												
Characteristic resistance	$V_{Rk,s}^0$ [kN]	21	31	36	54	77	85	103	133	66	104	162
Factor according EN1992-4:2018, section 7.2.2.3.1	$k_7$ [-]	1,0										
Partial factor	$\gamma_{Ms}^{1)}$	1,29								1,5		
<b>Concrete pry-out failure</b>												
Factor according EN1992-4:2018, section 7.2.2.4 without supplementary reinforcement	$k_8$ [-] <sup>2)</sup>	2,0										
Partial factor	$\gamma_{Mc}^{1)}$	1,5										
<b>Concrete edge failure</b>												
Effective length of anchor	$l_f = h_{ef}$ [mm]	$h_{nom} - t_h + t^{3)}$										
Effective outside diameter	$d_{nom} = d$ [mm]	10	12	13	16	19	20	22	25	16	20	25
Partial factor	$\gamma_{Mc}^{1)}$	1,5										

1) In absence of other national regulations

2) In case of supplementary reinforcement, the factor  $k_8$  should be multiplied with 0,75

3) For simple anchors (For doubled anchors resp. short anchors see Fig. 2 resp. Fig. 3, Annex B3)

**Table 8: Displacements under shear**

WELDA® Anchor Type		W1 – W5								W6		
Nominal size	d [mm]	10	12	13	16	19	20	22	25	16	20	25
Displacements $\delta_{v0}^{1)}$ to 1,5 mm under following loads in [kN]	$V_{1,5mm}$ [kN]	15	18	20	30	45	50	60	75	30	50	75
1) The indicated displacements $\delta_{v0}$ are valid for short-term loading, the displacements $\delta_{v\infty}$ can be increased under long term loading to 2,0 mm.												

### Combined tension and shear load

The factor  $k_{11}$  according EN1992-4:2018 section 7.2.3.2:  $k_{11} = 2/3$

**WELDA®**

Performance data  
Characteristic resistance and displacements under shear load, combined tension and shear load

**Annex C2**